

In the Claims:

This listing will replace all prior versions and listing of claims in the subject application.

1. (Currently Amended) A biodegradable nonwoven web having a permeability within the range of about 500 to about 1500 μm^2 and a void volume that is greater than about 25 cm^3/gram , wherein the web comprises

a. a first biodegradable binder fiber that does not undergo severe heat shrinkage and

b. a second biodegradable thermoplastic fiber having a melting temperature at least about 20°C. higher than the melting temperature of the first biodegradable binder fiber, and wherein the biodegradable nonwoven web is thermally bonded at a temperature within about 20° C above the melting temperature of the first biodegradable binder fiber, using only convective heating to thoroughly bind the web and to achieve the permeability and void volume.

2. (Previously Presented) The nonwoven web of claim 1, wherein the first biodegradable binder fiber is a multicomponent fiber comprising a surface component and a non-surface component.

3. (Previously Presented) The nonwoven web of claim 2, wherein the surface component has a melting temperature at least about 10°C less than the melting temperature of the non-surface component.

4. (Previously Presented) The nonwoven web of claim 3, wherein the second thermoplastic fiber has a melting temperature at least about 20°C. higher than the melting temperature of the surface component of the multicomponent fiber.

5. (Previously Presented) The nonwoven web of claim 3, wherein the surface component comprises L,D-polylactide (LD-PLA), or a polylactide-caprolactone copolymer.

6. (Previously Presented) The nonwoven web of claim 3, wherein the surface component comprises L,D-polylactide (LD-PLA), the non-surface component comprises polylactide, and the surface component has a lower L:D ratio than the non-surface component.
7. (Previously Presented) The nonwoven web of claim 2, wherein the multicomponent fiber is a bicomponent sheath/core fiber.
8. (Previously Presented) The nonwoven web of claim 7, wherein the sheath is 95:5 L:D polylactide, or a polylactide-caprolactone copolymer, and the core is 100% L-polylactide.
9. (Previously Presented) The nonwoven web of claim 1, wherein the first fiber exhibits an amount of shrinkage, at a temperature of about 70° C., that is less than about 10 percent.
10. (Previously Presented) The nonwoven web of claim 1, wherein the second fiber is selected from the group consisting of lower alkyl cellulose esters, starch, polyvinyl alcohol (PVA), chitosan, and PHBV (copolymer of polybetahydroxy butyrate and betahydroxyvalerate).
11. (Previously Presented) The nonwoven web of claim 10, wherein the lower alkyl cellulose ester is cellulose acetate.
12. (Previously Presented) The nonwoven web of claim 1, further having a contact angle less than 80 degrees, and wherein the contact angle is due to intrinsic properties of the fibers.
13. (Previously Presented) The nonwoven web of claim 1, comprising from about 40% to 95% of the first fiber, and from about 60% to 5% of the second fiber.

14. (Previously Presented) The nonwoven web of claim 1, wherein the web is produced by a bonded carded web process using through-air bonding.
15. (Previously Presented) An absorbent article comprising a surge layer made from the nonwoven web of claim 1.
16. (Withdrawn) The absorbent article of claim 15, comprising a liquid-permeable topsheet, a backsheet attached to the liquid-permeable topsheet, an absorbent structure positioned between the liquid-permeable topsheet and the backsheet, and wherein the surge layer is positioned between the topsheet and the absorbent structure.
17. (Previously Presented) The nonwoven web of claim 1, wherein the nonwoven web is thermally bonded at a temperature within about 10°C above the melting temperature of the first biodegradable binder fiber.
18. (Previously Presented) The nonwoven web of claim 1, wherein the nonwoven web is thermally bonded at a temperature within about 5°C above the melting temperature of the first biodegradable binder fiber.
19. (Previously Presented) The nonwoven web of claim 1, wherein the second biodegradable thermoplastic fiber does not melt.
20. (Previously Presented) The nonwoven web of claim 2 wherein the nonwoven web is thermally bonded at a temperature 10° to 15° C above the melting temperature of the surface component of the first biodegradable binder fiber.
21. (Previously Presented) The nonwoven web of claim 2 wherein the nonwoven web is thermally bonded at a temperature 5° to 10° C above the melting temperature of the surface component of the first biodegradable binder fiber.

22. (Previously Presented) The nonwoven web of claim 2 wherein the nonwoven web is thermally bonded at a temperature 2° to 5° C above the melting temperature of the surface component of the first biodegradable binder fiber.
23. (Canceled)
24. (Previously Presented) The nonwoven web of claim 1, wherein the first biodegradable binder fiber and the second biodegradable thermoplastic fiber, each have a fiber length of at least about 25 millimeters.
25. (Previously Presented) The nonwoven web of claim 1, wherein the first biodegradable binder fiber and the second biodegradable thermoplastic fiber, each have a fiber length of about 25 to 50 millimeters.
26. (Previously Presented) The nonwoven web of claim 2, wherein the nonwoven web is thermally bonded using a bonded carded web process.
27. (Currently Amended) A biodegradable nonwoven web having a permeability within the range of about 500 to about 1500 μm^2 and a void volume that is greater than about 25 cm^3/gram , wherein the web comprises a first biodegradable binder fiber that does not undergo severe heat shrinkage and a second biodegradable thermoplastic fiber having a melting temperature at least about 20°C. higher than the melting temperature of the first biodegradable binder fiber; and
wherein the biodegradable nonwoven web is thermally bonded at a temperature within about 5°C below the melting temperature of the first biodegradable fiber, using only convective heating to thoroughly bind the web and to achieve the permeability and the void volume.
28. (Previously Presented) The nonwoven web of claim 27, wherein the first biodegradable binder fiber is a multicomponent fiber comprising a surface component and a non-surface component.

29. (Previously Presented) The nonwoven web of claim 28, wherein the nonwoven web is thermally bonded at a temperature 2 to 5 °C below the melting temperature of the surface component of the first biodegradable binder fiber.